

# HumiSeal<sup>®</sup> 1A27LU Urethane Conformal Coating

## Technical Data Sheet

HumiSeal<sup>®</sup> 1A27LU is a single component, polyurethane conformal coating, suitable for general printed circuit board applications. HumiSeal<sup>®</sup> 1A27LU contains no free isocyanates and fluoresces under UV light for ease of inspection. HumiSeal<sup>®</sup> 1A27LU coating is RoHS Directive 2002/95/EC compliant and recognized under UL File Number E105698.

### Properties of HumiSeal<sup>®</sup> 1A27LU

Density, per ASTM D1475	0.96 ± 0.02 g/cm <sup>3</sup>
Solids Content, % by weight per Fed-Std-141, Meth. 4044	50 ± 3 %
Viscosity, per Fed-Std-141, Meth. 4287	1700 ± 200 centipoise
VOC	480 grams/litre
Recommended Coating Thickness	25 - 75 microns
Drying Time to Handle, per Fed-Std-141, Meth. 4061	25 minutes
Optional Curing Conditions to Reach Optimum Properties	30 days at RT 30 hours @ 76°C 20 hours @ 88°C
Recommended Thinner	HumiSeal <sup>®</sup> Thinner 521, 521EU
Recommended Stripper	HumiSeal <sup>®</sup> Stripper 1063
Shelf Life at Room Temperature, DOM	24 months
Thermal Shock, 50 cycles per MIL-I-46058C	-65°C to 125°C
Coefficient of Thermal Expansion - TMA	170 ppm/°C
Glass Transition Temperature - DSC	28°C
Modulus - DMA	18.1 MPa
Flammability, per UL 94	V-0
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Breakdown Voltage, per ASTM D149	7500 volts
Dielectric Constant, at 1MHz and 25°C per ASTM D150-98	3.6
Dissipation Factor, at 1MHz and 25°C per ASTM D150-98	0.02
Insulation Resistance, per MIL-I-46058C	2.0 x 10 <sup>14</sup> ohms (200TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	1.2 x 10 <sup>10</sup> ohms (12GΩ)

### Application of HumiSeal<sup>®</sup> 1A27LU

Cleanliness of the substrate is of extreme importance for the successful application of a conformal coating. Surfaces must be free of moisture, dirt, wax, grease, flux residues and all other contaminants. Contamination under the coating could cause problems that may lead to assembly failures.

#### Dipping

Depending on the complexity, density and configuration of components on the assembly, it may be necessary to reduce the viscosity of HumiSeal<sup>®</sup> 1A27LU with HumiSeal<sup>®</sup> Thinner 521 or 521EU in order to obtain a uniform film. Once optimum viscosity is determined, a controlled rate of immersion and withdrawal (5-15 cm/min) will further ensure even deposition of the coating and ultimately a uniform film. During the application, evaporation of solvent causes an increase in viscosity that should be adjusted by adding small amounts of HumiSeal<sup>®</sup> Thinner 521 or 521EU. Viscosity in the dip tank should be checked regularly, using a simple measuring device such as a Zahn or Ford viscosity cup.

## HumiSeal® 1A27LU Technical Data Sheet

### Spraying

HumiSeal® 1A27LU can be sprayed using conventional spraying equipment. Spraying should be done in an environment with adequate ventilation so that the vapour and mist are carried away from the operator. The addition of HumiSeal® Thinner 521 or 521EU is necessary to ensure a uniform spray pattern resulting in pinhole-free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used and operator technique. The recommended ratio of HumiSeal® 1A27LU to HumiSeal® Thinner 521 or 521EU is 1:1 by volume; however the ratio may need to be adjusted to obtain a uniform coating.

### Brushing

HumiSeal® 1A27LU may be applied by brush with a small addition of HumiSeal® Thinner 521 or 521EU. Uniformity of the film depends on component density and operator's technique.

### Storage

HumiSeal® 1A27LU should be stored away from excessive heat or cold, in tightly closed containers. HumiSeal products may be stored at temperatures of 0 to 35°C. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32°C.

### Caution

Application of HumiSeal® Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

The solvents in HumiSeal® 1A27LU are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult MSDS/SDS prior to use.

## Contact HumiSeal®

### HumiSeal North America

201 Zeta Drive  
Pittsburgh, PA 15208  
USA  
Tel: +1 412-828-1500  
Toll Free (US only): 866-828-5470  
[sales@humiseal.com](mailto:sales@humiseal.com)

### HumiSeal Technical Center

295 University Avenue  
Westwood, MA 02090  
USA  
Tel: +1 781-332-0734  
Fax: +1 781-332-0703  
[techsupport@humiseal.com](mailto:techsupport@humiseal.com)

### HumiSeal Europe

505 Eskdale Road, IQ Winnersh  
Berkshire RG41 5TU  
UK  
Tel: +44 (0)1189 442 333  
Fax: +44 (0)1189 335 799  
[europesales@chasecorp.com](mailto:europesales@chasecorp.com)

### HumiSeal Europe Support

Tel: +44 (0)1189 442 333  
Fax: +44 (0)1189 335 799  
[europetechsupport@chasecorp.com](mailto:europetechsupport@chasecorp.com)

### HumiSeal S.A.R.L

4/6 Avenue Eiffel  
78420 Carrieres-Sur-Seine  
France  
Tel: +33 (0) 1 30 09 86 86  
Fax: +33 (0) 1 30 09 86 87  
[humiseal.sarl@chasecorp.com](mailto:humiseal.sarl@chasecorp.com)

### HumiSeal Asian Support

Tel: 852-9451-6434  
Fax: 852-2413-6289  
[asiatechsupport@humiseal.com](mailto:asiatechsupport@humiseal.com)

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.