

Ellsworth Adhesives Ltd (Tooling Solutions)

## **RAKU-TOOL® MB-0670**

### **Board Material**

# Polyurethane Board for Modeling

Unit 2 Langlands Avenue
Kelvin South Business Park,
East Kilbride, G75 0YG, United Kingdom.
Email: saleseurope@ellsworth.com
Phone: +44 (0)1355 231122
www.ellsworthadhesives.co.uk/tooling



© RAMPF Tooling Solutions GmbH & Co. KG

PC - Rev.-Status: 01- 2015/03/12

Page 1 of 2

#### **Key Properties**

- Fine surface structure
- · Easily shaped and machined
- Low coefficient of thermal expansion
- · Good dimensional stability

#### **Applications**

- Master models
- · Cubing models
- Patterns

#### **Mechanical Properties**

			MB-0670
Color	visual		Brown
Density	ISO 1183	g/cm <sup>3</sup>	ca. 0.67
Shore hardness D	ISO 868		60 – 65
Coefficient of thermal expansion	ISO 11359	10 <sup>-6</sup> K <sup>-1</sup>	50 – 55
Deflection temperature, HDT	ISO 75	°C	75 – 80
Compressive strength	ISO 604	MPa	15 – 20
Flexural strength	ISO 178	MPa	20 – 25

#### **Processing**

The product should have a temperature of 20°C – 25°C during processing.

#### **Packaging**

	1500 x 500 x 25 mm
	1500 x 500 x 30 mm
	1500 x 500 x 50 mm
RAKU-TOOL® MB-0670	1500 x 500 x 75 mm
	1500 x 500 x 100 mm
	1500 x 500 x 150 mm
	1500 x 500 x 200 mm

#### **Storage**

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

#### **RAKU-TOOL® MB-0670**

#### **Board Material**

Polyurethane Board for Modeling



© RAMPF Tooling Solutions GmbH & Co. KG

PC - Rev.-Status: 01- 2015/03/12

Page 2 of 2

#### **Handling Precautions**

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.

F +49.71 23. 93 42-1666

E tooling.solutions@rampf-gruppe.de

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.