RAKU-TOOL® WB-0691

Board Material

Epoxy Board for Tools & Molds

Unit 2 Langlands Avenue
Kelvin South Business Park,
East Kilbride, G75 OYG, United Kingdom.
Email: saleseurope@ellsworth.com
Phone: +44 (0)1355 231122
www.ellsworthadhesives.co.uk/tooling



© RAMPF Tooling Solutions GmbH & Co. KG

PC - Rev.-Status: 01- 2016/06/22

Page 1 of 2

Key Properties

- · Very fine surface structure
- · Excellent machinability
- Good dimensional stability
- Heat resistant up to 110°C

Applications

- Lay-up tools for low temperature tooling prepregs
- Vacuum forming molds
- Medium temperature applications

Mechanical Properties

			WB-0691
Color	visual		Light blue
Density	ISO 1183	g/cm ³	ca. 0.69
Shore hardness D	ISO 868		70 – 75
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	35 – 45
Deflection temperature, HDT	ISO 75	°C	100 – 110
Compressive strength	ISO 604	MPa	50 – 60
Flexural strength	ISO 178	MPa	25 – 35
Tensile strength	ISO 527	MPa	15 – 20

Processing

The product should have a temperature of 20°C – 25°C during processing.

Packaging		
	1500 x 500 x 50 mm	
•	1500 x 500 x 75 mm	
RAKU-TOOL® WB-0691	1500 x 500 x 100 mm	
	1500 x 500 x 150 mm	
	1500 x 500 x 200 mm	

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

RAKU-TOOL® WB-0691

Board Material

Epoxy Board for Tools & Molds



© RAMPF Tooling Solutions GmbH & Co. KG

PC - Rev.-Status: 01- 2016/06/22

Page 2 of 2

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.

RAMPF Tooling Solutions GmbH & Co. KG Robert-Bosch-Str. 8-10 | D-72661 Grafenberg T +49.71 23. 93 42-1600

F +49.71 23. 93 42-1666

E tooling.solutions@rampf-gruppe.de

www.rampf-gruppe.de

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.